

TUB121N Polyethylene Copolymer

TUB121N is a natural bimodal high density polyethylene copolymer designed for extrusion of potable water, natural gas, industrial and mining pipe. When blended with an approved black concentrate, the resulting formulation (“TUB121”) is listed by the Plastics Pipe Institute (PPI TR-4, as both PE 4710 and PE 100) and is certified to ANSI/NSF Standards 14 and 61, CSA B137.1 and CSA B137.4.

Typical Properties¹

	Values		ASTM Method
	English Units	SI Units	
Resin			
Density	—	0.949 g/cc	D4883
Melt Index 190°C/5.0 kg	—	0.30 g/10 min	D1238
Melt Index 190°C/ 21.6 kg	—	8.5 g/10 min	D1238
Compression Molded Sample			
Tensile Strength (2 in/min)			D638
@ Yield	3,500 psi	24.1 MPa	
@ Break	4,400 psi	30.3 MPa	
Elongation (2 in/min)			D638
@ Yield	10.4 %	10.4 %	
@ Break	>600 %	>600 %	
Flexural Modulus			D790A
2% Secant	130,000 psi	900 MPa	
Notched Izod Impact Strength	12 ft-lbf/in	63 kJ/m ²	D256
Hardness			D2240
Shore D	64	64	
Vicat Softening Point	259 F	126 C	D1525
Brittleness Temperature	<-180 °F	<-118 °C	D746
Environmental Stress Crack Resistance			D1693
Condition C, 100 % Igepal, F50 (hrs.)	>5,000	>5,000	
Hydrostatic Design Basis ²			D2837
@ 23 C	1,600 psi	11.0 MPa	
@ 60 C	1,000 psi	6.9 MPa	
Minimum Required Strength (MRS) ⁴	1,450 psi	10.0 MPa	ISO 9080/12162
Notch Tensile (PENT) (hrs.)	>10,000	>10,000	F1473
Oxidation Induction Time			D3895
@ 210 C	>20 min	>20 min	
Thermal Stability	>464 F	>240 C	D3350
Cell Classification	445574C ²	445576C ²	D3350
Oxidative Resistance Classification	CC3	CC3	D3350

¹ Typical properties will vary and are not to be used for specification purposes.

Revision: 2/8/2017

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. As conditions of use may vary and are beyond the control of INEOS Olefins & Polymers USA, no representations or warranty, express or implied, are made with respect to the accuracy, reliability, or completeness of the this information. This information in no way modifies, amends, enlarges, or creates any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE HEREBY EXCLUDED. INEOS Olefins & Polymers USA shall not be responsible for any damage or injury resulting from abnormal use, from any failure to follow appropriate practices, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. This information relates only to the specific product and/or material designated and may not be valid for such product and/or material used in combination with any other product and/or material or in any process, unless otherwise specified. This information shall not be construed as a recommendation for any use that may infringe any patent, trademark, or the like, or as an endorsement of any material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA.

The name and logo INEOS are trademarks of the INEOS Group and its affiliated companies and businesses.

2600 South Shore Boulevard
League City, TX 77573
Tel: 281-535-6600
www.ineos-op.com

INEOS
Olefins & Polymers USA



TUB121N Polyethylene Copolymer

² Blended with approved black concentrate. Contact INEOS Technical Service for a list of approved concentrates.

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, call +1-800-527-5419.

Health and Safety Information

The product described herein may require precautions in handling and use because of toxicity, flammability, or other consideration. The Material Safety Data Sheet (MSDS) contains the available product health and safety information for this material and can be found at www.ineos-op.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

The Material Safety Data Sheet for this product contains shipping descriptions and should be consulted, before transportation, as a reference in determining the proper shipping description. If the material shipped by INEOS is altered or modified, different shipping descriptions may apply and the MSDS of the original material should not be used.

For additional information, samples, pricing and availability, please contact:

INEOS Olefins & Polymers, USA

Marina View Building
2600 South Shore Boulevard
Suite 500
League City, Texas 77573
Phone: +1 281 535 6600
Fax: +1 281 535 6764
Customer Service: +1 800 527 5419
Tech Service: +1 800 338 0489
www.ineos-op.com

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. As conditions of use may vary and are beyond the control of INEOS Olefins & Polymers USA, no representations or warranty, express or implied, are made with respect to the accuracy, reliability, or completeness of the this information. This information in no way modifies, amends, enlarges, or creates any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE HEREBY EXCLUDED. INEOS Olefins & Polymers USA shall not be responsible for any damage or injury resulting from abnormal use, from any failure to follow appropriate practices, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. This information relates only to the specific product and/or material designated and may not be valid for such product and/or material used in combination with any other product and/or material or in any process, unless otherwise specified. This information shall not be construed as a recommendation for any use that may infringe any patent, trademark, or the like, or as an endorsement of any material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA.

The name and logo INEOS are trademarks of the INEOS Group and its affiliated companies and businesses.

2600 South Shore Boulevard
League City, TX 77573
Tel: 281-535-6600
www.ineos-op.com

INEOS
Olefins & Polymers USA